# WHITMORE'S

## **TECHNICAL DATA SHEET**

### MOLY DRY FILM LUBRICANT

Moly Dry Film Lubricant contains micro-fine  $MoS_2$  suspended in a liquid, quick-drying carrier. It bonds dry  $MoS_2$  powder to surfaces without heating or baking. When applied on any surface, it forms a tenacious coating in seconds. Molybdenum disulfide ( $MoS_2$ ) is a solid, dry-form lubricant with a coefficient of friction of only 0.03. Moly Dry Film Aerosol will bond to ferrous and nonferrous metals, plastics, ceramics, rubber, wood, etc. Moly Dry Film Aerosol exhibits excellent chemical and thermal stability and is inert to water, oil, alkalis, many acids, and solids.

Moly Dry Film Lubricant prevents galling, seizure, stick-slip, fretting, corrosion, and metal-to-metal contact. Moly Dry Film Aerosol is used wherever a dry lubricant is needed, particularly where temperatures are extreme or environments are hostile.

#### **BENEFITS**:

- QUICK-DRY BONDING dry to the touch in seconds.
- UNIVERSAL bonds to both ferrous and nonferrous metals.
- ENHANCES MACHINED SURFACES fills in microscopic irregularities on contact surfaces, thus reducing friction and wear.
- ENVIRONMENTALLY SAFE lead free.
- PREASSEMBLY excellent choice for use during break-in period to smooth contact surfaces and prolong component life.

#### **APPLICATIONS:**

Moly Dry Film Lubricant is recommended for threads, gears, dies, taps, chains, sprockets, cables, pulleys, power screws, chucks, steady rests, swivels, sleeve bearings, wrist pins, pistons, cylinder walls, valve stems, camshafts, bolts and screws, jigs and fixtures, plungers, polished rods, conveyors, acme screws, lathe beds, ways, valve plugs, and seats.

Apply Moly Dry Film Lubricant to truck shackles, brake anchor pins and bushings, piston rods, rings, sleeves, U-bolts, open chains and rollers, width adjustment screws on Tenter Frames, and all parts subject to dirt and corrosion.


Moly Dry Film Lubricant is more effective when applied to a clean dry surface.

ASTM #		TYPICAL CHARACTERISTICS
	% Volatiles	75
Gardener Method	<b>Density,</b> lb/gal @ 60°F (15.5°C)	0.92
	Dry Time, Minutes	2-3
	Usable Temperature Range after Evaporation, °F (°C)	800 (427)
	Solids	MoS <sub>2</sub>
	Color	Dark Grey - Black
	VOC Content, g/liter	380

CAUTION: FLAMMABLE

Do not spray onto hot surfaces. Use with adequate ventilation.

The above are average values. Minor variations which do not affect product performance are to be expected in normal manufacturing.



#### THE WHITMORE MANUFACTURING COMPANY

930 Whitmore Drive • P.O. Box 9300 • Rockwall, Texas 75087 • USA • (972) 771-1000 • Fax: (972) 722-2108 An ISO 9001, ISO/TS 16949, and ISO 14001 Registered Company • <u>http://www.whitmores.com</u>

Performance Under Pressure Since 1893

LIMITED WARRANTY: The Whitmore Manufacturing Company makes the Limited Express Warranty that at the date of delivery, its goods shall be free from defects in Whitmore's materials and workmanship and shall meet the express written statements of quality, if any, made by Whitmore in connection with the sale of the goods. Other than such Limited Express Warranty, there are no express warranties made with respect to the sale of goods and all implied warranties existing under the law are expressly disclaimed and negated, particularly, Whitmore NEGATES AND DISCLAIMS THE IMPLIED WARRANTY OF MERCHANTABILITY AND THE IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. All other liability, either in contract or tort, including without limitation, strict liability found in Section 402A of the Restatement of Torts or otherwise, is negated and disclaimed. The sole remedy for Whitmore's breach of such Limited Express Warranty shall be a refund of the purchase price of its goods, and Whitmore shall have no responsibility for incidental or consequential damages sustained as a result of the use of the goods, whether sustained to the goods themselves or to other property. Data listed are subject to usual manufacturing variations.